

PRODUCT DATA SHEET

Pulastic[®] GM-700**2 Component Polyurethane****DESCRIPTION**

Solvent free, 2-component polyurethane manufactured by a company certified according ISO 9001 for quality management, ISO 14001 for environmental care and ISO 26000 for corporate sustainability.

USES

The nature of the product requires (manufacturer) trained specialists to execute the installation.

CHARACTERISTICS / ADVANTAGES

Pulastic GM 700 is a hard durable high quality compound, which is mainly used for the installation of seamless sports flooring systems, where load distribution is required. We recommend that the manufacturer is consulted regarding alternative applications other than the standard sports flooring systems. The material has a high hardness, a very high mechanical strength and a good flexibility, resulting in a high impact resistance. Moreover the compound has good bonding properties, is non-flammable and shows no shrinkage after curing. A good flow is assured due to the low viscosity liquid consistency. The material has good de-aerating properties.

PRODUCT INFORMATION

Packaging	Two-can sets of 20 Kg B component can be supplied in 21,2 Kg drums
Shelf life	Under ideal storage conditions the shelf-life, in original factory sealed cans, is A component 6 months and B component 12 months.
Storage conditions	Store material in a dry, cool (15-25C) environment where protection against damage is guaranteed. Avoid prolonged storage at temperatures below 5C or above 30C. Prolonged vibration and higher ambient temperatures during transportation can result in settling of the A Component, which makes mixing more difficult. Prolonged storage at low temperatures can result in crystallizing of the B component.
Colour	In accordance with manufacturers list of standard colours: Grey-White, Light-Grey, Middle Grey (504/506), Iron Grey (507), Light Blue (305), Middle Blue (307/308), Dark Blue (306/309), Light Green (401), Dark Green (400/417)
Density	1,40 Kg/litre

TECHNICAL INFORMATION

Shore D Hardness	67 Shore D	(DIN 53505)
Tensile strength	20 N/mm ²	(DIN 53455, sample 4, 200mm/min)
Tensile strain at break	100%	(DIN 53455, Sample 4, 200mm/min)

APPLICATION INFORMATION

Mixing ratio	Ratio A : B = 79 : 21 (weight).
Consumption	Approximately 1.400 grams/m ² for every mm thickness. A minimum of 1 mm is necessary to assure good self-levelling properties.
Material temperature	10°C to 30°C.
Ambient air temperature	10°C to 30°C.
Relative air humidity	max 80%.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

Consult the manufactures "Material Safety Data Sheet". Follow the instructions on the labels.

EQUIPMENT

Measuring-cup (in case of 21,2 Kg drums), mixing-blade, low-speed 1.000 Watt electric drill, Sieve, Swedish-knife, flat- or notched-trowel.
Clean all tools with PULASTIC Thinner 5C05 immediately after use !

SUBSTRATE PREPARATION

The substrate should be level (max. deviation 3 mm under a 3 m straight edge) and free from dirt, dust and moisture. Sanding or other treatment of the substrate may be necessary, to obtain good bonding. Take all the necessary safety precautions. Check availability and condition of materials and equipment. Check if the B component is free of crystallization. Should crystals be found the B component has to be heated to 40 °C and rolled or shaken until all crystals re-dissolve.

MIXING

Premix the A Component and check for lumps. Add the complete contents of the B Component and mix A and B thoroughly to a homogeneous mixture. Do not dilute ! Pour the mixture in a second drum (through a sieve 0,5-1 mm in case lumps are found in the A component) and mix for a further few seconds to avoid the use of unmixed material (from the sides and bottom of the first drum). To gain the maximum flow properties the full contents of the mixture should be poured out as quickly as possible (within the pot-life) and should be spread out immediately.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product

Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NEDERLAND B.V.

Pulastic sports flooring
Duurstedeweg 7 · 7418 CK DEVENTER
P.O. Box 420
7400 AK DEVENTER · The Netherlands
Phone: +31 570 620744
www.sika.nl / www.pulastic.com

PRODUCT DATA SHEET

Pulastic® GM-700
July 2022, Version 01.01
020812040020000049